

## TECHNICAL DATA

### Aramide needlefelt with Aramide scrim

Material	Nomex
Area Weight [g/m <sup>2</sup> ]	550
Thickness [mm]	2.1 ± 0.1
Air Permeability	13 ± 2 cm <sup>3</sup> /cm <sup>2</sup> /s @125Pa
Tensile Strength	
Length [Kgf]	>130
Cross [Kgf]	>150
Temperature Resistance	
Cont. [°C]	200
Peaks [°C]	230
Mullen Burst	40 kg/cm <sup>2</sup>
Special Treatment	Acid protective Water and Oil repellent Singed one side