

| | | | |
|------------------------------------|--|---------|-------|
| Chemical Analysis 化学成份 | SiO ₂ | | 62.00 |
| | Al ₂ O ₃ | | 25.50 |
| | MgO | | 0.20 |
| | CaO | | 0.10 |
| | Fe ₂ O ₃ | | 0.70 |
| | TiO ₂ | | 0.40 |
| | K ₂ O | | 0.70 |
| | Na ₂ O | | 0.20 |
| | I.O.L. | | 10.00 |
| Particle Size Distribution 粒度分布 | (wt%) | <20 μ m | 92 |
| | | <10 μ m | 77 |
| | | <5 μ m | 65 |
| | | <2 μ m | 47 |
| | | <1 μ m | 36 |
| Modulus of Rupture 断裂系数 | Dried at 110°C kgf/c m ² | | 40 |
| | | | |
| Whiteness 白度 | Fired at 1070°C % | | 79 |
| | Fired at 1180°C % | | 80 |
| Shrinkage 收缩率 | Fired at 1070°C % | | 3.0 |
| | Fired at 1180°C % | | 5.0 |
| Water Absorption 吸水率 | Fired at 1070°C % | | 18.0 |
| | Fired at 1180°C % | | 13.5 |

Product form:

Cake form product, moisture content about 25%+/-2 块状，水份含量 25%+/-2

Since the product is based on naturally occurring raw materials, data shown above are for reference only. Slight variation may occur.

陶瓷原料乃天然物質，以上数据會有輕微變動。